

## Fast-Covering HDPE

HDPE roll + adhesive tape. Having been treated for paint adhesion, this product ensures perfect masking of floors and all kinds of surfaces while painting.



### ADVANTAGES AND PERFORMANCES

- Professional masking
- Adhesion to surfaces with light pressure

### PHYSICAL PROPERTIES

		test method
Thickness:	10 µm	
Mass density (23 °C):	0,949 - 0,957 g/cm <sup>3</sup>	ISO 1183
MFI (190 °C - 5,0 kg):	0,28 - 0,38 g/10 min	ISO 1133
MFI (190 °C - 21,6 kg):	08 - 11 g/10 min	ISO 1133
Yield strength:	24 MPa	ISO 527
Tensile strength:	35 MPa	ISO 527
Heat distortion temperature:	75 °C	ISO 306
Heat strength:	< -80 °C	ASTM D 1709
Shore D hardness:	60	ISO 868

### MECHANICAL PROPERTIES

		test method
Maximum tensile strength:	MD 35 MPa - TD 40 MPa	ISO 527
Tear resistance:	MD 150 mN - TD 400 mN	ISO 6383-2
Maximum elongation:	MD 300 % - TD 400 %	ISO 527
Dart drop impact:	from 150 to 200 g	ASTM D 1709

The above values are the result of arithmetic averages from tests on sample productions and are not legally binding.

### ADHESIVE TAPE

Paper adhesive tape for professional masking; suitable for applications at medium temperatures in the car body repair, building and construction industries.

**Backing:** 59 g/m<sup>2</sup> impregnated white paper      **Adhesive:** natural dry rubber and solvent resins

### TECHNICAL PROPERTIES

Total thickness:	125 µm
Elongation at break:	8,5 %
Tensile strength:	75 N/25 mm
Adhesion to steel:	4 N/25 mm
Temperature resistance:	up to 80 °C for 30 minutes

The above values are the result of arithmetic averages from tests on sample productions and are not legally binding.

### ARTICLES, DIMENSIONS AND BARCODES

	dimensions	pieces per box	barcode
cod. 1706:	55 cm x 20 m	60	8051499033194
cod. 1707:	110 cm x 33 m	20	8051499033200
cod. 1708:	140 cm x 33 m	20	8051499033217
cod. 1709:	180 cm x 20 m	20	8051499033224
cod. 1710:	210 cm x 20 m	20	8051499033231
cod. 1710B:	240 cm x 16 m	20	8051499033248
cod. 1711:	270 cm x 16 m	20	8051499033255
cod. 1711B:	300 cm x 16 m	20	8051499033262

The a.m. values may be changed at any moment for production needs or technical updates.

rev. 01\_May 2019