

## Duct 300-S

PE laminated cloth tape with natural rubber adhesive. Thanks to its high adhesive force, it's excellent for the car body repair industry, for all kinds of repairs and tools, sealing and packaging, protection of surfaces and do-it-yourself applications.



### ADVANTAGES AND PERFORMANCES

- Good adhesiveness on irregular surfaces.
- Waterproof.
- Removable without tearing.
- Hand tearable.

### TECHNICAL PROPERTIES

		tolerance	test method
Backing:	PE laminated with polyester		
Adhesive:	natural rubber and solvent resins		
Total thickness:	300 µm	± 10 %	AFERA 5006
Tensile strength:	min. 16,5 N/25mm		PSTC 31
Elongation at break:	min. 11,5 %		PSTC 31
Adhesion to steel:	min. 10 N/25mm		AFERA 5001
Temperature resistance:	from -20 °C up to +80 °C		
Colour:	silver and black. Others on request		

The above values are the result of arithmetic averages from tests on sample productions and are not legally binding.

### ARTICLES, DIMENSIONS AND BARCODES

	dimensions	pieces per box	barcode
Duct 300-S silver:	48 mm x 25 m	24 rolls	8051499033996
Duct 300-S silver:	50 mm x 25 m	24 rolls	8051499034009
Duct 300-S black:	48 mm x 25 m	24 rolls	8051499034313
Duct 300-S black:	50 mm x 25 m	24 rolls	8051499034320

### OUR PROPOSAL OF PACKAGING

- Sleeve with coloured half moon label.

### RECOMMENDATIONS

It's a good rule to use the product within 6 months from purchase, because the unwinding force of the tape increases with time. The product must be stored in its box in a dry location protected from sunlight, at about 15 °C - 25 °C and 50% relative humidity. If stored in different conditions, the product must be reconditioned. After application, the removal of the tape must be done slowly without tears. Before applying the tape, always check if the surface is clean. Euromask disclaims any liability for any direct or indirect damage coming from the misuse of the product. Under normal conditions, the tape is not toxic and is not approved for medical use.

The a.m. values may be changed at any moment for production needs or technical updates.



rev. 01\_Jan 2024