

PP A 45

PP tape with acrylic adhesive, suitable for long-term storage of light weights and for professional and do-it-yourself applications.



ADVANTAGES AND PERFORMANCES

- Good adhesiveness on irregular surfaces.
- For manual and automatic use.

TECHNICAL PROPERTIES

		tolerance	test method
Backing:	BOPP		
Adhesive:	water-based acrylic emulsion		
Total thickness:	48 µm	± 5 %	
Film thickness:	28 µm		
Tensile strength:	min. 32 N/cm		AFERA 5004
Elongation at break:	min. 120 %		AFERA 5004
Adhesion to steel:	min. 4,5 N/cm		AFERA 5001
Temperature resistance:	room temperature		
Colour:	brown, white and transparent		

The above values are the result of arithmetic averages from tests on sample productions and are not legally binding.

ARTICLES, DIMENSIONS AND BARCODES

	dimensions	pieces per box	barcode
PP A 45 my brown noisy:	50 mm x 66 m	36 rolls	8051499032272
PP A 45 my brown noisy:	50 mm x 132 m	36 rolls	8051499032289
PP A 45 my white noisy:	50 mm x 66 m	36 rolls	8051499032296
PP A 45 my white noisy:	50 mm x 132 m	36 rolls	8051499032302
PP A 45 my transparent noisy:	50 mm x 66 m	36 rolls	8051499032319
PP A 45 my transparent noisy:	50 mm x 132 m	36 rolls	8051499032326

OUR PROPOSAL OF PACKAGING

- Sleeve with B/W or coloured (up to 5 colours) barcode label.
- Harmonica.
- Tower.

RECOMMENDATIONS

It's a good rule to use the product within 6 months from purchase, because the unwinding force of the tape increases with time. The product must be stored in its box in a dry location protected from sunlight, at about 15 °C - 25 °C and 50% relative humidity. If stored in different conditions, the product must be reconditioned. After application, the removal of the tape must be done slowly without tears. Before applying the tape, always check if the surface is clean. Euromask disclaims any liability for any direct or indirect damage coming from the misuse of the product. Under normal conditions, the tape is not toxic and is not approved for medical use.

The a.m. values may be changed at any moment for production needs or technical updates.



rev. 01_Jan 2024